



Shenzhen Upcera Dental Technology Co., Ltd  
5th Floor, Tsinghua IT Port R&B Bldg. B, Shenzhen,  
Guangdong, China

+86 755-8882-0818  
sales@upcera.com  
dental.upcera.com



Reliable Materials Expert

# PRODUCT CATALOG

Meet All Your Need



CE

ISO13485

FDA

Health Canada

KFDA

GOST

# PMMA



- Excellent abrasion resistance and no deformation
- Available for single shade and multi-shaded

Technical Parameter	Parameter	Value
	Flexural strength	≥100MPa
	Water absorption value	≤40μg/cm <sup>3</sup>
	Dissolved value	≤7.5μg/cm <sup>3</sup>

Chemical Composition	Component	Percentage
	Methacrylic acid polymer	~99%
	Pigment	≤1%

Specification	Type	Shades
	S (Monochrome)	A1 A2 A3 A3.5 A4 B1 B2 B3 B4 C1 C2 C3 C4 D2 D3 D4 Pink1/2/3 Clear
	M (Multilayer)	A1 A2 A3 A3.5 A4 B1 B2 B3 B4 C1 C2 C3 C4 D2 D3 D4

